

TEST (*)	STANDARD	DETERMINATION	Units.	FINISHES				
				Silk ⁽³⁾	Satin ⁽⁴⁾	Decorpolished ⁽⁵⁾	Ultrasoft	Riverwashed
Dimensions and Surface Appearance Determination	ISO 10545-2	Thickness ⁽¹⁾	mm	± 0,5 (5%)	± 0,5 (5%)	± 0,5 (5%)	± 0,5 (5%)	± 0,5 (5%)
		Slab Width Flatness Tolerance	mm	± 2 (0,1%)	± 2 (0,1%)	± 2 (0,1%)	± 2 (0,1%)	± 2 (0,1%)
		Slab Length Flatness Tolerance	mm	± 4 (0,1%)	± 4 (0,1%)	± 4 (0,1%)	± 4 (0,1%)	± 4 (0,1%)
		Slab Dimensional Tolerance ⁽²⁾	mm	± 2 (0,6%)	± 2 (0,6%)	± 2 (0,6%)	± 2 (0,6%)	± 2 (0,6%)
Water Absorbtion	ISO 10545-3	Boiling Absorption ⁽¹⁾	%	0,01-0,1	0,01-0,1	0,01-0,1	0,01-0,1	0,01-0,1
		Apparent Density	gr/cm ³	2,4 (±5%)	2,4 (±5%)	2,4 (±5%)	2,4 (±5%)	2,4 (±5%)
Impact Resistance	ISO 10545-5	Coefficient of Restitution	-	0,8	0,8	0,6	0,8	0,8
Resistance to Deep Abrasion	ISO 10545-6	Lost Volume	mm ³	-	130	-	-	-
Resistance to surface abrasion	ISO 10545-7	Visual Appearance	Class	PEI IV	PEI IV	PEI III	PEI III	PEI IV
Coefficient of Linear Thermal Expansion	ISO 10545-8	From 25°C to 100°C	10 ⁻⁶ . °C ⁻¹	5,7	5,7	5,7	5,7	5,7
Thermal Shock Resistance	ISO 10545-9	Damage	-	Not Damaged	Not Damaged	Not Damaged	Not Damaged	Not Damaged
Moisture Expansion	ISO 10545-10	Coefficient of Dilatation	mm/m	< 0,1	< 0,1	< 0,1	< 0,1	< 0,1
Frost Resistance	ISO 10545-12	Damage	-	Not Damaged	Not Damaged	Not Damaged	Not Damaged	Not Damaged
Chemical Resistance	ISO 10545-13	Cleaning Products	Class	GA	UA	GA	GA	GA
		Pool Chemicals	Class	GA	UA	GA	GA	GA
		Low Concentrations	Class	GLA	ULA	GLB	GLA	GLA
		High Concentrations	Class	GHA	UHA	GHB	GHA	GHA
Stain Resistance	ISO 10545-14	Visual Appearance	Class	5	5	5	4	5
Lead and Cadmium Release	ISO 10545-15	Lead Concentration	mg/dm ²	<0,01	<0,01	<0,01	<0,01	<0,01
		Cadmium Concentration	mg/dm ²	<0,001	<0,001	<0,001	<0,001	<0,001
Light Fastness	DIN 51094	Chromatic Change	-	No Change	No Change	No Change	No Change	No Change

(1) Non-mesh slabs

(2) Cut to size format slabs

(3) Slate

(4) Iron, Steel touch

(5) Nanotech

(*) Slippery test according to CE certificate

TEST	STANDARD	DETERMINATION	Units	Thickness			
				6	6+	12	20
Weight	-	-	kg/m ² (**)	14,4	14,8	28,8	48,0
Bending Strength	ISO 10545-4	Breaking Strength	N	>1100	>1100	>5000	>15000
		Modulus of Rupture	N/mm ²	>45	>45	>45	>45

(**) ±5%